

STANDARD : BS6088

TYPE	DIAMETER (um)	PERCENT (%)
BS6088 A	> 1180	0-3
	1180-850	5-20
	850-425	65-95
	<425	0-10
BS6088 B	>850	0-5
	800-600	5-20
	600-300	30-75
	300-180	10-30
	<180	0-15

TYPE	MESH	DIAMETER (um)	PERCENT (%)
JT/T446-2001 一号	>20	>850	0
	20-30	850-600	3-50
	30-50	600-300	30-80
	50-140	300-106	10-40
	140<	<106	0-5
JT/T446-2001 二号	>30	>600	0
	30-50	600-300	40-90
	50-100	300-150	5-60
	100<	<150	0-5

AASHTOM247

TYPE	DIAMETER (um)	PERCENT (%)
AASHTO M247 I 号	>850	0
	850-600	5-25
	600-300	60
	300-150	15-20
	<150	0-5
AASHTO M247 II 号	>600	0
	600-425	0-10
	425-300	25-40
	300-180	50-70
	<180	0-5

KS

TYPE	MESH	DIAMETER (um)	PERCENT (%)
ks1	>20	>850	0
	20-30	850-600	3-50
	30-50	600-300	30-80
	50-140	300-106	10-40
	140<	<106	0-5
KS2	>30	>600	0
	30-50	600-300	40-90
	50-100	300-150	5-60
	100<	<150	0-5

EN1423/1424

EN 1424 (DROPPING ON)	DIAMETER (um)	MESH	PERCENT (%)
	> 1180	16 上	0-10
	1185-850	16-20	5-30
	850-600	20-30	40-80
	600-425	30-40	80-100
	425-250	40-60	95-100
EN 1423 (MIXING)	> 710	25 上	0-2
	710-600	25-30	0-10
	600-355	30-45	30-70
	355-212	45-70	70-100
	212-125	70-120	95-100

TYPE	MESH	DIAMETER (um)	PERCENT (%)
GBT 24722-2009 1 号	>20	>850	0
	20-30	850-600	3-50
	30-50	600-300	30-80
	50-140	300-106	10-40
	140<	<106	0-5
GBT 24722-2009 2 号	>30	>600	0
	30-50	600-300	40-90
	50-100	300-150	5-60
	100<	<150	0-5

GBT 24722-2009 3 号	>70	>212	0
	<140	<90	0-4

TECHNICAL DATA

Size gradation	
Refractive index	≥1.5
Roundness	>80%
Specific weight	approx. 2.5 g/cm ³
Bulk weight	approx. 1.6 kg / l
Coating	silane
Packaging	plastic bags (or paper bags)
Storage	dry and sheltered

Composition and Information on dangerous ingredients

Chemical Composition (%)

SiO ₂	: 73.00
Na ₂ O	: 14.30
K ₂ O	: 0.60
CaO	: 9.20
MgO	: 4.00
Fe ₂ O ₃	: 0.11
Al ₂ O ₃	: 2.00
SO ₃	: 0.30