



210008349216



中国认可
国际互认
检测
TESTING
CNAS L1561

检测报告

TEST REPORT

No: AJ00694496-001

样品名称
Sample Name

板状刚玉

委托单位
Client Name

Luoyang Zhongsen Refractory Co., Limited

检测类别
Test Kind

委托检验

国家磨料磨具质量检验检测中心
National Quality Inspection & Testing Center for Abrasives
郑州磨料磨具磨削研究所有限公司磨料磨具实验室
Grinding Abrasives Laboratory of Zhengzhou Research Institute for Abrasives & Grinding Co., Ltd.
郑州磨料磨具磨削研究所有限公司
Zhengzhou Research Institute for Abrasives & Grinding Co., Ltd.

注 意 事 项

Remarks

1.无本机构公章或检验检测专用章的报告无效。

The report is invalid without the official seal or the special seal for inspection and testing.

2.无主检(或编制)、批准人签字或签章的报告无效。

The report is invalid without the signature or signature of the chief inspector (or the editor) and the authorized person.

3.未重新加盖本机构公章或检验检测专用章的复制报告无效。

Duplication of the report is invalid without re-stamping the official seal or the special seal for inspection and testing.

4.涂改的报告无效。

The report is invalid if altered.

5.委托方若对报告有异议，应于收到报告之日起十五日内向本机构提出。

If there is any objection for the report, please raise it to Zhengzhou Research Institute for Abrasives & Grinding Co., Ltd. within 15 days since receiving this report.

6.本机构仅对送检样品的检测数据负责。

The organization is only responsible for the test data of submitted samples.

7.委托方须对所提供样品的全部相关信息，资料和样品的真实性负责。

The clients should be responsible for the authenticity of all related information, documents, and sample.

8.委托方须在收到报告之日起三个月内领回受检样品，逾期，本机构不负保管责任。

The samples should be taken back within 3 months since the clients receive the report, otherwise Zhengzhou Research Institute for Abrasives & Grinding Co., Ltd. is not responsible for the preservation of the samples.

9.以上条款若与国家相关规定抵触，按国家相关规定执行。

If the clauses above are in conflict with the relevant regulations of the state, the relevant regulations of the state should be implemented.

10.若无特别说明，检测地点均为地址A。

Unless otherwise specified, the testing location is always address A.

国家磨料磨具质量检验检测中心
National Quality Inspection & Testing Center for Abrasives

郑州磨料磨具磨削研究所有限公司磨料磨具实验室
Grinding Abrasives Laboratory of Zhengzhou Research Institute for Abrasives & Grinding Co., Ltd.

郑州磨料磨具磨削研究所有限公司
Zhengzhou Research Institute for Abrasives & Grinding Co., Ltd.



www.cagtic.cn

地址A：中国·郑州市高新技术开发区梧桐街121号

Add: No.121, Wutong Street, Hi-Tech Development Zone, Zhengzhou City, Henan Province, China.

地址B：中国·郑州市高新技术开发区春兰路22号

Add: No.22, Chunlan Road, Hi-Tech Development Zone, Zhengzhou City, Henan Province, China.

联系电话：0371-86067915 86067916

Tel for business : +86-371-86067915 86067916

投诉电话：0371-67657910

Tel for complaint : +86-371-67657910

传真：0371-67658535

Fax : +86-371-67658535

电子邮箱：market@cagtic.cn

E-mail : market@cagtic.cn

郑州磨料磨具磨削研究所有限公司
国家磨料磨具质量检验检测中心
检测报告

No:AJ00694496-001

第 1 页 共 2 页

样品名称 Sample Name		板状刚玉	规格型号 Specification	1-3
委托单位 Client	名称 Name	Luoyang Zhongsen Refractory Co.,Limited		
	地址 Address	Yaowan Village,South Dukang Road,Yichuan County,Luoyang,Henan Province,P.R.CHINA		
送样人 Sample Sender	LUO	联系电话 Phone	0379-69351288	
		电子邮箱 E-mail	/	
样品原编号 Sample Original Number	/	商标 Trademark	/	
生产日期 Production Date	/	用途 Application	/	
样品状态 Sample Status	粉末颗粒状	样品数量/质量 Quantity/Mass	/	
到样日期 Received Date	2023-10-16	检测日期 Testing Period	2023-10-16至2023-10-17	
判定依据 Judgment Basis	仅出具数据，不做判定。			
检测结果 Test Result(s)	不判定			
备注 Remarks	/			
编制 Edited by	侯宇		批准 Approved by	张中峰
签发日期 Issued Date	2023年10月17日		(Seal for Inspection & Testing)	

注：‘/’表示该项内容空缺。NOTE：“/” means no content.

郑州磨料磨具磨削研究所有限公司
国家磨料磨具质量检验检测中心
检测报告

No:AJ00694496-001

第2页 共2页



检测项目 Test Item(s)	单位 Unit	检测结果 Test Result(s)	检测依据 Test Method
灼减	%	0.10	GB/T 3044-2020
SiO ₂	%	0.01	GB/T 3044-2020
Fe ₂ O ₃	%	0.01	GB/T 3044-2020
CaO	%	0.01	GB/T 3044-2020
Al ₂ O ₃	%	99.56	GB/T 3044-2020
K ₂ O	%	0.01	GB/T 3044-2020
Na ₂ O	%	0.29	GB/T 3044-2020
体积密度	g/cm ³	3.64	GB/T 2997-2015
显气孔率	%	1.7	GB/T 2997-2015

以下空白
End of Report